



ALPHA Q130

Non-Trimnable Butyl Tape

UPDATED 8/23/16

Product Overview: ALPHA Q130 is a versatile, high performance gasket tape formulated to provide optimal levels of adhesion, elongation, and tensile strength. ALPHA Q130 is a non-drying compound that features excellent resistance to water, weather, and air intrusion and adheres well to all non-porous substrates.

Product Uses: ALPHA Q130 is well suited for use in the following applications: weatherproofing in marine and RV assemblies, roof seam sealing, construction of curtain wall panels, and duct sealing.

Technical Information:

Raw Material Base	Rubber Based Mastic	Odor	Odorless
Cone Penetration	10.5 – 11.5 mm (77°F)	Tensile Strength	12 – 14 PSI
Color	White, Gray, Black	Service Temp. Range	-40° – 180°F
Specific Gravity	1.55 – 1.65	Application Temp. Range	-5° – 120°F
Solids	100%	Physical State	Solid
Elongation (ASTM D412)	>800%	Manufactured State	Extruded Rolls
QUV Exposure	Surface Discoloration Only	Shelf Life	12 Months

Application Information: ALPHA Q130 material is extruded onto removable release paper backing to facilitate handling. For most efficient usage, it is recommended that the material be pressed onto one surface, stripped of its paper backing, and then brought into contact with the second surface. When using to seal applications involving fasteners, position on the entry side to prevent the penetration of contaminants through fastener holes.

Safety Instructions: No special requirements are needed. Consult the product SDS for detailed safety information.

Contact Us: For more information regarding this product and others, please contact us at:

Alpha Systems LLC
5120 Beck Drive
Elkhart, IN 46516

Phone: 1-574-295-5206
Fax: 1-574-970-2703
www.alphallc.us

RESIDENTIAL HOUSING · RVS/UTILITY TRAILER · HVAC ·
COMMERCIAL/INDUSTRIAL ROOFING · MARINE · MOBILE/MODULAR · METAL BUILDING

Disclaimer: The information presented herein has been compiled from sources considered to be accurate and reliable, but is not guaranteed to be so. In practice, the differences in materials, substrates, storage conditions, actual site conditions and other factors outside of Alpha Systems control are such that Alpha Systems assumes no liability, nor makes any warranty, express or implied for such information, recommendations or instructions related to its products. It is the users responsibility to determine the suitability of any material for a specific purpose and to adopt such safety precautions as may be necessary.